

# Decal Print 90.140 P Windows Graphic

Made in 

Perforated Monomeric Vinyl 90 µm Glossy, Removable Adhesive

## Roll Size

Z4017L - 980mm x 50m | Z4017L.1 - 1370mm x 50m

## Product Description

Perforated PVC film, 90 µ Thick, Calendered and manufactured with monomeric resins

Excellent printing quality and stability, to solvents

Especially design for printing and applications on flat transparent surfaces e.g. Car glasses, Buses, Trains and windows decoration

## Technical Data Sheet

PVC			
Test Method	Physical Properties	Average Value	Tolerance
	Thickness	90 µm	
	Tensile Strength	≥ 22 N/mm <sup>2</sup>	
	Tear Resistance	150 Mpa	
	Glossiness	50	
	Shrinkage	< 1,1%	
	Perforation: diameter/distance	1,8 mm/2,55mm	
Adhesive			
Type	Clear Removable Acrylic		
Weight	55 g/m <sup>2</sup>		
Test Method	Physical Properties	Average Value	Tolerance
FINAT (25 mm/22°C/N)	Peel Adhesion	1 - 2 (initial)	± 5%
		8 - 10 (24h)	± 5%
FINAT (1"/22°C/h)	Shear Test	10 - 15	± 5%
Liner			
Type	Clay Coated Paper		
Weight	140 g/m <sup>2</sup>		
Features			
	Temperature	Relative Moistness	
Printing	15 - 25 °C	20 - 50%	
Storage	10 - 35°C	< 60%	
Drying Time	Handling (min)	20	
	Finishing/Application (h)	4 - 8	
Finishing	Cold or Hot lamination; Glossy/Matt surface		

Note: Surfaces where material is going to be applied, must be completely clean of dirt, fat or any other contamination that can affect its adhesion. Compatibility of application surfaces must be tested by the user before applying the material.

The data contained in this information are based on our knowledge and practice experience. It intends to be an information source and it does not constitute a guarantee. Due to the enormous variety of possible uses, the user/purchaser should carefully consider the suitability and performance of the product for each intended use and shall assume the risks regarding such use. Digidelta shall not be liable for losses or damages to third parties.



[www.dec-al-adhesive.eu](http://www.dec-al-adhesive.eu)

**DECAL**  
THINK GREEN!

DECAL its a Trademark, of Digidelta Internacional, SA

Edificio Digidelta - Zona Industrial - 2350-483 Torres Novas - Portugal / Tel: (+351) 249 819 160 - Fax: (+351) 249 812 422